

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 1 160 822 A1

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:
05.12.2001 Bulletin 2001/49

(51) Int Cl.7: H01J 29/28

(21) Application number: 01401361.9

(22) Date of filing: 23.05.2001

(84) Designated Contracting States:
AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE TR
Designated Extension States:
AL LT LV MK RO SI

(30) Priority: 23.05.2000 JP 2000151141

(71) Applicant: SONY CORPORATION
Tokyo (JP)

(72) Inventors:
• Fujita, Koji
Shinagawa-ku, Tokyo (JP)
• Ohno, Katsutoshi
Shinagawa-ku, Tokyo (JP)
• Nomura, Kazumasa
Shinagawa-ku, Tokyo (JP)


(74) Representative: Thévenet, Jean-Bruno et al
Cabinet Beau de Loménie
158, rue de l'Université
75340 Paris Cédex 07 (FR)

(54) Transfer film, method fabricating thin film for display apparatus panel using the transfer film, and display apparatus having thin film fabricated by the method

(57) A transfer film (20) capable of transferring thin films such as a conducting film (3a), a heat absorption film (3b) onto a display apparatus panel, a method for fabricating thin films for a display apparatus panel using the transfer film (20), and a display apparatus having thin films fabricated by the method are provided. The transfer film (20) is constructed by forming a conducting

film layer (3a) and an adhesion layer (4) on a base film (1). The transfer film (20) is disposed on the display apparatus, and a heat pressure adhesive bonding process is performed to transfer the conducting film layer (3a) to the display apparatus. A high quality display apparatus is realized by fabricating a high quality conducting film (3a) using the transferring process.

FIG.2



EP 1 160 822 A1

Description

BACKGROUND OF THE INVENTION

1. Technical Field of the Invention

[0001] The present invention relates to a transfer film, a method for fabricating a thin film for a display apparatus, and a display apparatus having the thin film fabricated by the method.

2. Description of the Related Art

[0002] In production of a color cathode ray tube panel, technology for fabricating so-called a metal back layer is widely employed. The metal back layer is fabricated by using an aluminum vacuum evaporation deposition process on a fluorescent substance layer formed on an inner surface of the panel so as to increase luminance of a color cathode ray tube. Furthermore, there is a technology (e.g. Japanese Patent Application laid-open No. 11-242939) for absorbing heat reflection from an aperture grille (shadow mask) by forming a black color layer on the aluminum deposition layer, i.e. inside of the metal back layer. Such technology is employed to prevent color shift caused by shifting of electron beam landing positions due to temperature drift. Such temperature drift may be caused by heating up of the aperture grille due to the electron beams bombardments.

[0003] Such technology will now be described with reference to Fig. 4 showing a cross sectional view of the color cathode ray tube construction. As shown in Fig. 4, a fluorescent substance layer 52 is formed on the inside surface of a color cathode ray tube panel 51 toward a side of an electron gun 61. A metal back layer 53 is formed with the aluminum vacuum evaporation deposition process so as to cover the inside fluorescent substance layer 52. Further, a black color layer 54 is formed to cover the inside surface of the metal back layer 53.

[0004] Fig. 4 shows a schematic view of a fluorescent substance layer 52 to help reader's understanding, and a detail construction is omitted. In practice, fluorescent substance stripes or fluorescent substance dots corresponding to colors representing red, green and blue are formed on predetermined positions of the black color layer 54 disposed inside the surface of the panel 51. Then, an intermediate layer is provided to smooth a surface on which the fluorescent substance stripes or fluorescent substance dots are mounted.

[0005] The black color film 54 absorbs heat radiation generated at the aperture grille 55 disposed near the metal back film 53 and heated up due to electron beam bombardments. The black color film 54 is operable to prevent radiation/reflection from the inside surface of the metal back layer 53 to the aperture grille 55. Accordingly, a heat expansion coefficient of the aperture grille 55 is reduced.

[0006] In one of conventional methods for fabricating

the black color film 54, the metal back film 53 is formed with the aluminum vacuum evaporation deposition on each color cathode ray tube panel, and the black color film 54 is attached onto the metal back film 53 by spray painting of graphite solved in organic solvent. In other conventional method, the black color film 54 of aluminum oxide is fabricated by performing another aluminum vacuum evaporation deposition process with a higher pressure (about 0.1-0.01 Torr) than that of the first aluminum vacuum evaporation deposition process to form the metal back film 53.

SUMMARY OF THE INVENTION

[0007] There are drawbacks in the color cathode ray tube panel fabrication method in which the above-cited methods are used for forming the metal back film or the black color film.

[0008] The spray painting method is implemented since graphite has a low evaporation pressure and is difficult to use for the vacuum evaporation deposition process. However, there are drawbacks such as variation of film thickness and the film tends to peel off easily. It seems difficult to form a good graphite film (black color film) which can resolve those drawbacks. Furthermore, in the spray painting method, the graphite may penetrate into the fluorescent substance layer when there are some cracks in the aluminum deposition film (metal back film) whereby black spots or color drifts are generated.

[0009] In the aluminum oxide black color film (blackened film) fabrication method with performing the second aluminum vacuum evaporation deposition after forming the aluminum deposition film, there is an advantage of that the fabrication process of the aluminum metal back film and the fabrication process of the aluminum oxide black color film for heat absorption may be performed in the same production apparatus by simply changing processing pressure. On the other hand, there are effects of residual gases in the production apparatus and interferences among deposition molecules evaporated from a plurality of thermal evaporation sources since the evaporation process takes place in low pressure vacuum. These effects may cause variation of the black color film disposed on the inside surface of the panel. Such variation in the thickness of the black color film may cause luminescent variation of the color cathode ray tube and deterioration of image quality.

[0010] There is another conventional method for fabricating magnesium film or barium film. However, it is difficult to perform a stable film deposition unless pressures inside the panel and residual gas densities are carefully controlled when the magnesium film or the barium film is fabricated.

[0011] In all of the conventional methods described above, the entire film deposition process is separately performed for each color cathode ray tube panel. For example, in order to fabricate the aluminum metal back

film, the panel is placed inside a vacuum chamber having a color cathode ray tube panel mounting stage, and then the vacuum chamber is evacuated. After the vacuum chamber is vacuumed, aluminum disposed inside the vacuum chamber is heated to evaporation, and the metal back film of aluminum is formed inside the panel. After the metal back film is formed, the panel is removed from the vacuum chamber, and another panel is set in turn in the vacuum chamber. Then, a series of process starting from the vacuuming of the vacuum chamber is repeated again. Accordingly, considerable manpower is required.

[0012] The present invention is made by considering the above-cited situation. An object of the present invention is to provide a transfer film capable of forming a thin film on a panel of display apparatus such as a color cathode ray tube. Another object of the present invention is to provide a method for fabricating a thin film for a display apparatus panel by using a transfer film. Still another object of the present invention is to provide a display apparatus having a thin film fabricated by the method according to the present invention.

[0013] In accordance with an embodiment of the present invention, a transfer film constructed by forming a conducting film layer and an adhesion layer on a base film is provided. The transfer film enables to form a high quality conducting film layer on the display apparatus panel.

[0014] In accordance with another embodiment of the present invention, a transfer film constructed by forming a heat absorption film layer, a conducting film layer and an adhesion layer on a base film is provided. The transfer film enables to form a high quality heat absorption film layer and conducting film layer on the display apparatus panel.

[0015] The present invention enables to provide a method for fabricating a thin film for the display apparatus panel in which the transfer film constructed by forming a conducting film layer and an adhesion layer on a base film, or, the transfer film constructed by forming a heat absorption film layer, a conducting film layer and an adhesion layer on a base film is disposed on the display apparatus panel. The conducting film layer or a set of the conducting film layer and the heat absorption film layer is transferred to the display apparatus panel by heating and pressing the transfer film. According to the present invention, the high quality conducting film and/or heat absorption film may be fabricated.

[0016] The present invention enables to provide a display apparatus having the conducting film layer or a set of the conducting film layer and the heat absorption film layer transferred from the transfer film constructed by forming a conducting film layer and an adhesion layer on a base film, or, the transfer film constructed by forming a heat absorption film layer, a conducting film layer and an adhesion layer on a base film. According to the present invention, the image quality of the display apparatus may be promoted.

[0017] Other and further objects, features and advantages of the present invention will appear more fully from the following description.

5 BRIEF DESCRIPTION OF THE DRAWINGS

[0018]

Fig. 1 is an expanded cross sectional view showing a part of a transfer film in accordance with an embodiment of the present invention:

Fig. 2 is an expanded cross sectional view showing a part of a transfer film in accordance with another embodiment of the present invention:

Fig. 3 is a schematic cross sectional view showing apparatus for forming a thin film on a color cathode ray tube panel to explain another embodiment of the present invention: and

Fig. 4 is a schematic cross sectional view showing a construction of color cathode ray tube of the related art.

DESCRIPTION OF THE PREFERRED EMBODIMENTS

[0019] An embodiment of the present invention will now be described with reference to figures.

[0020] Fig. 1 is an expanded cross sectional view of a part of a transfer film in accordance with an embodiment of the present invention.

[0021] A transfer film 10 according to the present embodiment is constructed by forming a cushion layer 2, a conducting film layer 3a, adhesion layer 4 and a cover film 5 layer by layer on a base film 1 layer by layer.

[0022] The base film 1 may be a long film consisting essentially of, for example, polyethylene terephthalate (PET). A width of the film may be equal to or approximately equal to a height of front side plane of the color cathode ray tube, for example. A thickness of the base film 1 is not limited to any particular values in the present embodiment. For example, a thickness may be set to a value with which the film may endure against pulling tensile force along longitudinal direction of the film applied during the transferring process, which will be described below, whereby preventing accidents like cutting of the film.

[0023] The cushion layer 2 is formed on the base film 1. The cushion layer 2 is provided for helping the base film 1 to be peeled off easily from the conducting film layer 3a without damaging the conducting film layer 3a, and for alleviating vibrations from, for example, a pressing roller whereby preventing damage onto the conducting film layer 3a. Accordingly, the cushion layer 2 is fabricated so as to exhibit stronger adhesiveness at a contacting surface with the base film 1 and weaker adhesiveness at a contacting surface with the conducting film layer 3a. A thickness of the cushion layer 2 is not limited to a particular value in the present embodiment. For ex-

ample, the thickness of the cushion layer 2 may be set to an arbitrary value as long as impacts of the pressing roller is included in consideration.

[0024] The conducting film layer 3a is formed on the cushion layer 2. The conducting film layer 3a composes the metal back film by transferring itself onto the luminescent substance layer disposed inside surface of the color cathode ray tube, for example. The conducting film layer 3a may be formed with aluminum vacuum evaporation process.

[0025] The adhesion layer 4 is formed on the conducting film layer 3a. The adhesion layer 4 is adhered to the inside of the color cathode ray tube by heating and being pressed.

[0026] The cover film 5 is formed on the adhesion layer 4. The cover film 5 is provided for protecting the adhesion layer and for easier handling of the transfer film 10.

[0027] The transfer film 10 of the present embodiment may be fabricated in-line with a predetermined method while the long base film 1 being continuously transported. Accordingly, the aluminum deposition film composing the conducting film layer 3a may be fabricated in a quality as high as the aluminum deposition film can keep a mirror surface condition with no damage like cracks.

[0028] Fig. 2 is an expanded cross sectional view showing a part of a transfer film in accordance with another embodiment of the present invention.

[0029] A transfer film 20 of the present embodiment has the same construction as that of the transfer film 10 shown in Fig. 1 except that the conducting film layer 3a is formed on a thermal absorption film layer 3b and that the absorption film layer 3b is formed on the cushion layer 2 of the transfer film 10 shown in Fig. 1. The same construction elements as that of Fig. 1 are designated the same numerals as Fig. 1, and operations and effects of these redundant elements are not discussed in the following description.

[0030] The cushion layer 2 is fabricated so as to exhibit stronger adhesiveness at a contacting surface with the base film 1 and weaker adhesiveness at a contacting surface with the thermal absorption film layer 3b. Accordingly, The cushion layer 2 and the heat absorption film layer 3b can be separated easily.

[0031] The heat absorption film layer 3b has a function of absorbing heat from the aperture grille when the heat absorption film layer 3b is transferred and disposed onto the color cathode ray tube panel with the conducting film layer 3a. The heat absorption film layer 3b may be formed as the black color film by using the spray painting of graphite.

[0032] The transfer film 20 of the present embodiment may be fabricated in-line with a predetermined method while the long base film 1 being continuously transported, in the same as the transfer film 10 shown in Fig. 1. Accordingly, the black color film of graphite composing the heat absorption film layer 3b may be fabricated while keeping a constant film thickness, and the aluminum

deposition film composing the conducting film layer 3a may be fabricated with a quality as high as the aluminum deposition film can maintain the mirror surface condition.

5 [0033] A method for fabricating a thin film on the display apparatus panel using a transfer film in accordance with an embodiment of the present invention will now be described.

10 [0034] Fig. 3 is a schematic cross sectional view showing apparatus for forming the thin film on the color cathode ray tube panel for an explanatory purpose in accordance with the present embodiment.

15 [0035] As shown in Fig. 3, the transfer film 10 is mounted on a roller 31, and is taken up by a roller 32 via rollers 33, 34. In the present embodiment, the transfer film 10 is mounted in the roller 31 in such a way that the base film 1 is facing outward (upward direction in the figure) and the cover film 5 facing inward (downward direction in the figure). Accordingly, the base film 1 faces upward and the cover film downward when the transfer film 10 is transported from the roller 31 and transported toward the roller 32.

20 [0036] Rollers 35, 36 are disposed in a vicinity of the roller 33. The roller 35 is positioned to face the roller 33. The cover film 5 is peeled off from the transfer film 10 taken up from the roller 31 by separating at the adhesion layer 4, and rolled up by the roller 36 via the rollers 33, 35. Accordingly, the transfer film 10 exposing the adhesion layer 4 is transported to the rollers 34, 32.

25 [0037] In the present embodiment, there is tensile force applied on the transfer film 10 between the rollers 33 and 34. The tensile force may be applied, for example, by increasing a rotational friction coefficient of the roller 31 and/or a rotational drive force of the roller 32.

30 [0038] The apparatus for forming the thin film of the present embodiment comprises a base plate 37 and support members 38, 39, 38', 39'. The support members 38 and 38' are disposed along the lateral direction of the transfer film 10 (orthogonal direction to the page plane of Fig. 3) so as to face each others across the transfer film 10 with a separation distance the same as or approximately the same as a width of the transfer film 10. The support members 39, and 39' are similarly disposed. Plate members 40 and 41 are disposed between the support members 38, 38' and the support members 39, 39', respectively. The plate members 40 and 41 have an L-shaped cross section and are connected to the support members 38-38' and the support members 39-39' so as to allow a turning motion of the plate members 40 and 41.

35 [0039] A pressing roller 42 essentially consisting of silicon material is disposed above the support members 38-38' and the support members 39-39'. The pressing roller 42 is supported by any appropriate members so as to allow motions of the pressing roller 42 along an up/down direction and horizontal direction between the support members 38(38'), 39(39'). Further, a transportation apparatus 43 is disposed on the base plate 37

between the support members 38(38'), 39(39'). The transportation apparatus 43 moves along a direction transverse to the transfer direction of the transfer film 10 (e.g., from the front side to the back side of the page in Fig. 3). The transportation apparatus 43 carries a color cathode ray tube panel 44 with its inner surface 44a facing upward to a point directly below the transfer film 10. The florescent substance layer is formed on the inner surface 44a of the color cathode ray tube panel 44, and is not shown in the figure.

[0040] The transportation apparatus 43 moves directly below the transfer film 10, and stops at a position in which width edge positions of the transfer film 10 and corresponding width edge positions of the color cathode ray tube panel 44 are aligned. After the transportation apparatus 43 has stopped, the plate members 40, 41 turn toward the color cathode ray tube panel 44. Positions of the plate members 40, 41 after the turning of the plate members 40, 41 are indicated by dotted lines in Fig. 3. With the turning of the plate members 40, 41, the transfer film 10 is pulled down by the plate members 40, 41 to the inner surface 44a of the color cathode ray tube panel 44, and the adhesion layer 4 of the transfer film 10 comes into contact with the inner surface 44a of the color cathode ray tube panel 44. A position of the transfer film 10 after the turning of the plate members 40, 41 is indicated by a dotted line in Fig. 3. Then, the pressing roller 42, which is heated up to a predetermined temperature (e.g., 100 °C), is lowered to press the transfer film 10. The pressing roller 42 is rolled while applying a predetermined pressure (e.g., 1 kg/cm²) on the inner surface 44a from one peripheral part of the color cathode ray tube panel 44 to the other peripheral part (e.g., right hand side to left hand side of Fig. 3). Accordingly, the transfer film 10 is bonded with the inner surface 44a of the color cathode ray tube panel 44 by the thermal pressure adhesive bonding process of the adhesion layer 4.

[0041] When the pressing roller 42 reaches to the end, i.e. the other peripheral part (the left side of Fig. 3 in this example) of the color cathode ray tube panel 44, the roller 42 is elevated and the plate members 40, 41 turn upward to return to the initial positions. In the present embodiment, a shape and/or diameter of the pressing roller 42 may be selected to appropriate values so as that the transfer film 10 can be uniformly heated and performed the pressure adhesive bonding process on the whole area of the inner surface 44a of the color cathode ray tube panel 44.

[0042] A constant tensile force is applied on the transfer film 10 between the rollers 33 and 34. The cushion layer 2 of the transfer film 10 is adhered to the base film 1 and the conducting film layer 3a, and has weaker adhesive strength with the conducting film layer 3a whereby the cushion layer 2 may be easily separated from the conducting film layer 3a. Accordingly, the base film 1 and the cushion layer 2 of the transfer film 10 are separated from the conducting film layer 3a and back to the original position shown with real line in Fig. 3 when the

pressing roller 42 is elevated and the plate members 40, 41 are returned to the initial positions. The conducting film layer 3a remains on the inner surface 44a of the color cathode ray tube panel 44 due to the adhesion layer 4 whereby realizing transfer and attachment of the conducting film layer 3a from the transfer film 10 to the color cathode ray tube panel 44.

[0043] In the above, it is described the method of fabricating the conducting film on the color cathode ray tube panel 44 by transferring and attaching the conducting film layer 3a from the transfer film 10 shown in Fig. 1. A similar method may be used for fabricating the heat absorption film and the conducting film on the color cathode ray tube panel from the transfer film 20.

[0044] In the method fabricating the heat absorption film and the conducting film, the transfer film 20 shown in Fig. 2 instead of the transfer film 10 shown in Fig. 1 is mounted on the roller 41 of Fig. 3. The transfer film 20 is mounted so as that a side of the base film 1 faces upward and a side of the cover film 5 downward. The cover film 5 is taken up by the roller 36, and the rest of the transfer film 20 is taken up by the roller 32 via the rollers 33, 34. The heat absorption film layer 3b and the conducting film layer 3a may be transferred and attached on the inner surface 44a of the color cathode ray tube panel 44 by a similar method as the method used for the heat pressure adhesive bonding process of the conducting film layer 3a of the transfer film 10.

[0045] Operations and process relating to the transferring process described above, such as transportation of the color cathode ray tube panel 44, rolling up of the transfer film 10 or 20, operations of the pressing roller 42 and plate members 40, 41, are controlled and executed by a control apparatus and a drive apparatus (not shown in the figure), respectively, as a series of operation and process in accordance with a predetermined sequence.

[0046] According to the embodiments of the present invention, the transfer film is configured in such a way that the cushion layer 2, the graphite heat absorption film layer 3b, the aluminum conducting film layer 3a, the adhesion layer 4, and the cover film 5 are formed layer by layer. Accordingly, the film layers may be fabricated with a high quality. For example, the aluminum conducting film layer may be able to maintain the mirror surface condition, a distribution of film thickness of the graphite heat absorption film layer may be kept uniform, and so on. Further, according to the embodiments of the present invention, these high quality heat absorption film layer 3b and the conducting film layer 3a may be transferred on the cathode ray tube panel. Temperature drifts may be alleviated since the heat absorption film layer 3b has the uniform film thickness distribution.

[0047] The cushion layer 2 is disposed so that the heat absorption film layer 3b or the conducting film layer 3a is weakly adhered with the cushion layer 2 whereby the base film 1 may be easily separated at the cushion layer 2. In the transferring process, the heat absorption

film layer 3b or the conducting film layer 3a may be easily separated from the base film 1 and the cushion layer 2 when the base film 1 is separated from the heat absorption film layer 3b or the conducting film layer 3a with the cushion layer 2 due to the tensile force applied on the base film 1. Accordingly, the heat absorption film layer 3b or the conducting film layer 3a may be transferred and bonded to the color cathode ray tube panel 44 without causing any damages such as cracks on these layers.

[0048] In a conventional method for fabricating the aluminum conducting film on the color cathode ray tube panel, more manpower is required since the aluminum vacuum evaporation deposition process is performed by setting of each color cathode ray tube panel inside a vacuum evaporation apparatus separately, exhausting gases to vacuum, and heating up of a source heater. On the other hand, the transferring process in accordance with the embodiments of the present invention enables fabricating the heat absorbing film 3b or the conducting film 3a with only a small amount of manpower since the transferring process is performed by using the heat pressure adhesive bonding process while the pressing roller 12 being rolled from one peripheral part to the other peripheral part of the color cathode ray tube panel 44.

[0049] In the transferring process, operations such as transportation of the color cathode ray tube panel, rolling up of the transfer film, lowering of the pressing roller, scan rolling of the pressing roller, disposing of the transfer film to the inner surface of the panel by turning of the plate members, elevating of the pressing roller, are executed as a series of operations in accordance with a predetermined sequence. Accordingly, efficient operations may be realized, and a productivity may be promoted in manufacturing the color cathode ray tube.

[0050] According to the embodiments of the present invention, the conventional intermediate film to maintain the mirror surface condition of the aluminum conducting film 3a formed on the inner surface 44a of the color cathode ray tube panel 44 may be eliminated whereby drawback relating to the intermediate film may be resolved. Further, the productivity of the color cathode ray tube panel may be promoted since the step for fabricating the intermediate film can be eliminated.

[0051] Furthermore, the luminance may not be decreased and the temperature drift may be alleviated since the heat absorption film (graphite film) fabricated by the transferring process has a uniform film thickness distribution. Further, the luminance of the color cathode ray tube may be promoted since the conducting film (metal back film) can maintain the mirror surface condition. Accordingly, the color cathode ray tube with better image quality may be realized in accordance with the embodiments of the present invention.

[0052] The present invention is described for examples in which the present invention is applied on the color cathode ray tube panel. However, the present invention is not limited to such examples only, and can be

applied to other display apparatus such as plasma display panel (PDP). In such a case, the present invention enables to fabricate an electrode film (conducting film) by the transferring process of the present invention when the electrode film (conducting film) is formed on a panel substrate of the display apparatus.

[0053] According to the present invention, high quality conducting film, or, a set of high quality conducting film and the heat absorption film may be fabricated since the transfer film is configured so as that the conducting film, or, the conducting film and the heat absorption film is/are formed on the base film layer by layer.

[0054] Further, according to the present invention, the conducting film or heat absorption film with high quality may be fabricated since the conducting film layer or the heat absorption film layer is transferred by the heat pressure adhesive bonding process from the transfer film configured by forming the conducting film, or, the conducting film and the heat absorption film on the base film layer by layer.

[0055] Further, according to the present invention, a high quality display apparatus may be realized since the conducting film, or, the conducting film and the heat absorption film may be realized with a high quality in the cathode ray tube panel having the conducting film layer, or, a set of the heat absorption film layer and the conducting film layer transferred by the heat pressure adhesive bonding process from the transfer film in accordance with the present invention.

Claims

1. A transfer film (101) comprising:

a base film (1),
a conducting film layer (3a) formed on said base film (1), and
an adhesion layer (4) formed on said conducting film layer (3a).

2. A transfer film (20) comprising:

a base film (1),
a heat absorption film layer (3b) formed on said base film (1),
a conducting film layer (3a) formed on said heat absorption film layer (3b), and
an adhesion layer (4) formed on said conducting film layer (3a).

3. A method for fabricating a thin film for a display apparatus panel (44), comprising the steps of:

disposing a transfer film (10) on said display apparatus panel, said transfer film (10) being constructed by forming a conducting film layer (3a) on a base film (1) and an adhesion layer (4) on

said conducting film layer (3a), and
heating and pressing said transfer film (10; 20)
onto said display apparatus panel to transfer
said conducting film layer (3a) to said display
apparatus panel.

5

4. A method for fabricating a thin film for a display apparatus panel (44), comprising the steps of:

disposing a transfer film (20) on said display apparatus panel, said transfer film (20) being constructed by forming a heat absorption film layer (3b) on a base film (1), a conducting film layer (3a) on said heat absorption film layer (3b), and an adhesion layer (4) on said conducting film layer (3a), and
heating and pressing said transfer film (20) onto said display apparatus panel to transfer said heat absorption film layer (3b) and said conducting film layer (3a) to said display apparatus panel.

10

15

20

5. A display apparatus (44) comprising:

a conducting film (3a) fabricated by transferring from a transfer film (10) comprising a base film (1), a conducting film layer (3a) formed on said base film layer (1), and an adhesion layer (4) formed on said conducting film layer.

25

6. A display apparatus (44) comprising:

a conducting film (3a) and a heat absorption film (3b) fabricated by transferring from a transfer film (10) comprising a base film (1), a heat absorption film layer (3b) formed on said base film (1), a conducting film layer (3a) formed on said heat absorption film layer (3b), and an adhesion layer (4) formed on said conducting film layer (3a).

30

35

7. A method for fabricating a film for a display apparatus panel (44), comprising the steps of:

40

disposing a transfer film (10; 20) on said display apparatus panel, said transfer film (10;20) having said film to be attached on said display apparatus panel, and
heating and pressing said transfer film (10; 20) onto said display apparatus panel.

45

50

55

FIG.1




FIG.2




FIG. 3





FIG.4





European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 01 40 1361

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
X	US 5 639 330 A (OTAKE KEIICHI ET AL) 17 June 1997 (1997-06-17) * the whole document *	1-7	H01J29/28
X	EP 0 382 554 A (MATSUSHITA ELECTRIC IND CO LTD) 16 August 1990 (1990-08-16) * the whole document *	1-7	
X	US 5 418 075 A (UTSUMI ICHIRO) 23 May 1995 (1995-05-23) * the whole document *	1,3,5,7	
X	US 3 910 806 A (SCHWARTZ JAMES W) 7 October 1975 (1975-10-07) * the whole document *	1,3,5,7	
X	US 3 893 877 A (LIBMAN PHILOMENA C ET AL) 8 July 1975 (1975-07-08) * the whole document *	1,3,5,7	
X	DATABASE WPI Section EI, Week 199911 Derwent Publications Ltd., London, GB; Class V05, AN 1999-127343 XP002174604 & JP 11 003675 A (SONY CORP), 6 January 1999 (1999-01-06) * abstract *	1,3,5,7	TECHNICAL FIELDS SEARCHED (Int.Cl.7)
X	PATENT ABSTRACTS OF JAPAN vol. 014, no. 182 (E-0916), 12 April 1990 (1990-04-12) & JP 02 033825 A (NISSHA PRINTING CO LTD), 5 February 1990 (1990-02-05) * abstract *	1,3,5,7	H01J
-/--			
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 10 August 2001	Examiner Drouot-Onillon, M-C
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X: particularly relevant if taken alone Y: particularly relevant if combined with another document of the same category A: technological background O: non-written disclosure P: intermediate document</p> <p>T: theory or principle underlying the invention E: earlier patent document, but published on, or after the filing date D: document cited in the application L: document cited for other reasons & : member of the same patent family, corresponding document</p>			

EPC FORM 1503 (3/92) (P/4/021)



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 01 40 1361

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
X	PATENT ABSTRACTS OF JAPAN vol. 013, no. 439 (E-827), 3 October 1989 (1989-10-03) & JP 01 167933 A (NISSHA PRINTING CO LTD), 3 July 1989 (1989-07-03) * abstract *	1,3,5,7	
			TECHNICAL FIELDS SEARCHED (Int.Cl.7)
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 10 August 2001	Examiner Drouot-Onillon, M-C
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document			

EPC FORM 1523 03 02 (P/ALC01)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 01 40 1361

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

10-08-2001

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 5639330 A	17-06-1997	JP 3266339 A	27-11-1991
		DE 69129506 D	09-07-1998
		DE 69129506 T	01-10-1998
		EP 0446878 A	18-09-1991
		JP 5314932 A	26-11-1993
EP 0382554 A	16-08-1990	JP 2209487 A	20-08-1990
		JP 2064474 C	24-06-1996
		JP 3049131 A	01-03-1991
		JP 7095424 B	11-10-1995
		KR 9300390 B	16-01-1993
		US 5141461 A	25-08-1992
US 5418075 A	23-05-1995	JP 5234508 A	10-09-1993
		IT 1261195 B	09-05-1996
		KR 261795 B	15-07-2000
US 3910806 A	07-10-1975	CA 1053992 A	08-05-1979
US 3893877 A	08-07-1975	NONE	
JP 11003675 A	06-01-1999	NONE	
JP 02033825 A	05-02-1990	JP 1940342 C	09-06-1995
		JP 6064993 B	22-08-1994
JP 01167933 A	03-07-1989	JP 1901624 C	27-01-1995
		JP 6024097 B	30-03-1994

EPO FORM P0459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82